



(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:

12.03.1997 Bulletin 1997/11

(51) Int. Cl.⁶: A61M 29/00, A61K 9/70

(21) Application number: 95934320.3

(86) International application number:

PCT/JP95/02129

(22) Date of filing: 17.10.1995

(87) International publication number:

WO 96/11720 (25.04.1996 Gazette 1996/18)

(84) Designated Contracting States:

AT BE CH DE DK ES FR GB GRIE IT LI LU MC NL
PT SE

(72) Inventors:

- IGAKI, Keiji
Shiga 525 (JP)
- TAMAI, Hideo
Shiga 524 (JP)

(30) Priority: 17.10.1994 JP 250859/94

(71) Applicant: KABUSHIKIKAISHA IGAKI IRYO
SEKKEI

Kusatsu-shi, Shiga 525 (JP)

(74) Representative: Müller, Frithjof E., Dipl.-Ing.

Patentanwälte

TER MEER-MÜLLER-STEINMEISTER &
PARTNER


Mauerkircherstrasse 45

81679 München (DE)

(54) DRUG-RELEASING STENT

(57) A stent according to the present invention is adapted to be introduced into a vascular system such as blood vessels. The stent includes a stent body produced by weaving or knitting a fiber containing a drug and made of a low-melting biodegradable polymer into a tubular shape, or coating a drug-containing low-melting biodegradable polymer on a stent body. When the stent is introduced into the vascular system, the drug con-

tained therein is dosed in a locally limited region of the vascular system. The low-melting biodegradable polymer used has a melting point of 80° C or lower and is at least one compound selected from the group consisting of poly-ε-caprolactone, poly-D, L-deca-lactone, poly-dioxane and a copolymer thereof.

**FIG.1**